

# TL-0023 — Blistering and Pinholing of Fluid Applied Waterproofing Membranes Technical Letter (US Version)

Whenever liquid applied coatings are used over cementitious or other porous substrates, the possibility of blisters and/or pinholes exists. This phenomenon is caused by the expansion of moisture vapor and air that is trapped in the substrate (out-gassing). Blisters and/or pinholes are most likely to be generated on hot, sunny days when the initial temperature of the substrate is relatively low, but increases rapidly due to heat generated from direct sunlight on the membrane. The rapid increase in temperature converts the moisture in the substrate to the vapor phase and creates a vapor drive towards the source of the heat. Any air trapped in the substrate will also expand as it heats up.

There are many factors that influence the amount of moisture transmission and air expansion including temperature during coating application, change in temperature following application, humidity, moisture content of the concrete, concrete formulation, concrete age and surface porosity.

With BITUTHENE® Deck Prep and PROCOR® there are a number of techniques that can be used to reduce the level of blistering and pinholing experienced on-site. One effective technique is to adjust the application time to avoid conditions outlined above, i.e., applying the membrane later in the day or avoiding areas that are in direct sunlight. Some applicators have found it useful to apply a thin application or “scratch coat” of BITUTHENE®Deck Prep or PROCOR®(10-15 mil) to fill the surface irregularities and raise the surface temperature before application of the full membrane.

PROCOR®Concrete Sealer has been found to be the most effective and flexible way to minimize the possibility of blisters and pinholes in PROCOR®. This is a specially formulated water-based coating that is applied to the substrate by roller or spray prior to the full PROCOR®application. For a product use guide and full details of application procedures consult the PROCOR®Concrete Sealer Data Sheet.

Conclusion, care must be taken with all fluid applied waterproofing products when the substrate contains moisture or if there are voids in the substrate. However, the combination of the unique characteristics of BITUTHENE®Deck Prep and PROCOR®membranes coupled with an understanding of the mechanisms that create blisters and pinholes will allow projects to progress quickly with quality results.

[gcpat.com](http://gcpat.com) | North America Customer Service: 1 877-4AD-MIX1 (1 877-423-6491)

This document is only current as of the last updated date stated below and is valid only for use in the United States. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on [www.gcpat.com](http://www.gcpat.com). Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2019-03-11

[gcpat.com/solutions/products/bituthene-post-applied-waterproofing/tl-0023-blistering-and-pinholing-fluid](http://gcpat.com/solutions/products/bituthene-post-applied-waterproofing/tl-0023-blistering-and-pinholing-fluid)