

Ultratuff001 FC is a reinforced waterproofing deck membrane. It is liquid applied in-situ to adapt to the design and shape of the area being waterproofed

PROPERTIES

- High flexibility
- Quick drying
- High solid equals high film build
- High elongation
- Very good water resistance & early water resistance.
- Latex based
- Choice of colours if exposed.

RECOMMENDED USES:

- Decks, patio's, suspended decks (top coated with Flexiglaze)
- For use over concrete and well-fixed plywood
- Bathrooms under tiles
- Decks under tiles
- Upstand waterproofing
- Roofs (top coated with Flexiglaze)
- Window rebates (in block or masonry or plaster); (top coated with Flexiglaze)

LIMITATIONS:

All decks, roofs and floors should have a positive fall.
Exterior exposed areas (not covered) must be coated over with Flexiglaze.
Ensure good drying conditions during laying. Cross air movement is very important.

SURFACE PREPARATION: Concrete

Allow full 28 days cure time after the concrete pour. Acid etch, grind or shot blast to prepare the concrete prior to priming. Ensure surfaces are clean/dry and free from surface contaminants. Check falls and reset falls if necessary using Lockfast Floor Levelling Compound (FLC).



APPLICATOR INSTRUCTIONS

Application - Preparation Preliminary Work

Ensure that preliminary work, such as formation of falls and flashing rebates, grooves and ducts, provision of battens, rounded edges, fillets and overflows, installation of vents and countersinking edges and outlets, is complete and properly constructed to enable the Ultratuff 001 FC System to work as intended. This work and the substrate need to be smooth, clean and dry. Falls on roofs to be 1:30 and decks 1:40 and gutters 1:100 minimum; as proscribed by local bodies.

Confirm that the substrate, including falls, surface finish, fillets, sumps, countersinking terminations and projections, will permit Ultratuff 001 FC work of the required standard.

Concrete Substrate

Ensure concrete substrate is cured for a minimum of 14 days, graded to correct falls, wood float finish, no sharp edges, clean and free from debris. Cracks in the substrate are to be chased to allow for the application of the 15mm wide x 3mm deep Silicon Modified Paintable (SMP) bead of sealant (Simson ISR 70-50 supplied by Bostik) or similar, to act as a joint filler and bond breaker.

Plywood/ Compressed Sheet Substrate

Ensure that sheets have been butt jointed, staggered laid and fixed with stainless steel screws, glued across major supports to correct falls, are rigid with flush butt joints, no lumps or hollows, smooth, free of debris and dry. All upstands to be filleted, all downturns to have rounded edges rounded off and rainwater outlets countersunk as required for drainage.

Internal only Strandboard etc. Ensure this board has not deteriorated due to water exposure. Ensure that sheets have been butt jointed, staggered laid and fixed with screws, glued across major supports to correct falls, are rigid with flush butt joints, no lumps or hollows, smooth, free of debris and dry. Sanded smooth. All upstands to be filleted, all downturns to have rounded edges rounded off and rainwater outlets countersunk as required for drainage.

Applying Ultratuff 001 FC Membrane System

Priming

Apply a suitable metal anti-corrosion primer to all metal surfaces. Aquaguard 101 is applied to all substrates at a rate of 5-6 sqm/Lt - one coat.

Bonding agent

Subsequently, the Aquaguard 101 shall be primed, to ensure adhesion, with Allnex Duraseal.

Joint Reinforcing

All sheet joints are to be over-spatuled with 15mm wide smear of Silicon Modified Paintable (SMP) bead of sealant (Simson ISR 70-50 supplied by Bostik; or similar) to act as a joint control measure / semi-bond breaker. A coat of Ultratuff 001 FC is to be applied over the joint/crack area and a 100mm wide detail strip of 225g/m² fibreglass mat or reinforcing polyester cloth tape is to be rolled into the membrane. (Note the polyester cloth tape will dry **quicker** than fibreglass.) A coat of Ultratuff 001 FC is applied over the mat to completely saturate the mat and eliminate all pin holes.

Main Reinforcing layer

Apply the **first coat body** coat of Ultratuff 001 FC at 1.1m²/lt with a long nap roller cover. Allow to dry. Average drying time is 1 hour at 20°C in low humidity. If reinforcing mat is included in application average drying time is 3 hours at 20° in low humidity.

Embedded 1mm wide Reinforcing 300gsm CSM cloth can then be laid to all exterior areas including concrete substrates. (Optional, but recommended, for interior areas to be protected by Tiles and not subject to foot traffic where only a single layer of Reinforcing over junctions & joints is required.) The reinforcing mat or cloth is to be worked into the Ultratuff 001 FC body coat. The reinforcing mat or cloth should be free of lumps and furry patches. Use a laminating roller.

Pin holes and or shrinkage cracks must be filled with sealant before the application of the second coat. Application is to commence at floor to wall joints. A strip of 225g/m² fibre glass reinforcing mat 200-300 wide is to be bedded into the Ultratuff 001 FC which is to be applied to wall and deck surfaces.

The surface of PVC rainwater outlets shall be scuff sanded. The mat is to be laid over the outlet flange plate and turned down into the waste finishing with a clean edge.

NOTE WELL: The material should look and feel completely dry (reinforced membrane should be allowed to cure overnight) before the areas can be accessed or additional coats applied. Touch the surface with force to ensure the product has through-dried and has not just surface skinned-off. Humidity, non-porous surfaces, limited ventilation and temperatures below 20°C will increase drying times. Good cross air movement will assist drying.

The **second body coat of Ultratuff 001 FC** is to be applied at right angles to the first body coat at 1.5-2.0m²/t. A second coat is applied to completely saturate the mat. The mat is to be worked against the wall and deck surfaces and tightly into the junction with a brush to eliminate wrinkles, bridging and furring of the mat. When the second application of the Ultratuff 001 FC is complete and dry no pin holes, thin spots, perforations or lumps should be evident. A minimum of 1.2mm dry film thickness must be achieved.

Re-check for pinholes and/or shrinkage cracking in areas of heavy application. (E.g. internals and angles). If these exist, then "smear" fill them with sealant.

The optional anti-slip trafficable coating Ultratuff 001 FC is applied at the rate of 0.6 - 0.8 litre/m² with a goop loop or long nap roller cover to provide a texture.

Optional, for a very smooth finish: use another coat of Ultratuff 001 FC with surfacing tissue to create a finish that shows less of the mat visible.

If not covered in tiles, the **Ultratuff 001 FC must be over-coated**. The external trafficable UV stable top coat Flexiglaze can be applied by brush or roller to develop a minimum dry film build of 80 microns. The coating is to be applied by brush or roller at right angles to the previous coats. To ensure even consistent coverage, apply in two coats at 9m² / lt / coat.

Form, mould and flash all upstands, down turns and penetrations in accordance with the Ultratuff 001 FC technical specifications.

Movements Joints

Form and flash movement control joints as designed in accordance with the Allnex Technical Specifications.

Finishing

Finish all Ultratuff 001 FC laying, detailing, terminations and over flashings to a fully weatherproof condition, to ensure performance of the Ultratuff 001 FC installation as intended.

Foot Traffic

Foot traffic is not allowed on the Ultratuff 001 FC installation after laying until cured. Foot wear with high heels with narrow hard soles is not allowed.

Access Boards

Provide access boards and protection to Ultratuff 001 FC for later operations and remove when no longer needed.

Acceptance

Arrange for an inspection of the completed Ultratuff 001 FC work.

Subsequent Work

Make good any Ultratuff 001 FC cut or damaged by later work, by cutting out, filling in or overlaying damaged area with Ultratuff 001 FC application as required. Repairs can be neatly made in an Ultratuff 001 FC installation at any time.

Clean-up

Clean up as work proceeds. Utensils and minor spills can be cleaned with water if still wet. Cured material can be cleaned with Xylene.

Leave

Leave work to the standard required by following procedures, as described in the specification.

Remove

Remove debris, unused materials and elements from the site.

Tiling:

1. The surface must be clean and dry (can be Tiled 24hrs after final coat is completely dry, usually 48hrs)
2. The surface needs to be primed with
A> ASA Multiprime 2 part, in accordance with the ASA instructions.
B> or Allnex Neoprime
3. Suitable adhesives are
A> ASA Accelerflex mixed with ASA Fixall **or** ASA Conflex or
B> Unifloor
4. Grouting must be done after the adhesive has fully cured.
5. Movement joints must be provided as per the tiling standards.
6. Tile within seven days or lay a protection sheet over the membrane until tiling or covering.
7. Ensure membrane that is going to be left exposed once Tiles are laid is first protected by 2x coats of Flexiglaze.

Material usage


	Material	Coverage	Quantity for 100m ²	Units for 100m ²
Primer	Aquaguard 101	5-6m ² /lt	14lts	10 lt A + 10lt B
Bonding agent	Allnex Duraseal	7 m ² /lt	14	1 x 20lt
Body coat #1	Ultratuff 001 FC	1.1m ² /lt	90lt	6 x 15lts
Fiberglass mesh	300gsm Chopped strand mat	1m ²	100 m ²	1 roll
Body coat #2	Ultratuff 001 FC	1.5m ² /lt	65 lts	4 x 15lts
UV protection; if required.	Flexiglaze low sheen	8m ² / lt / coat; 2 coats required	12.5 lts	2 x 10lts
				(Total 10 x 15lt Ultratuff 001 FC)

PRODUCER STATEMENT AND GUARANTEE:

Allnex Ultratuff 001 FC is guaranteed for 15 years from the date of completion providing regular inspections are undertaken and re-glazed as appropriate, if necessary (every 5 years depending on wear). Specifically excluded is cracking in substrates, which exceeds the movement capability of the Ultratuff 001 FC system. The user should note that wrinkling or seaming is due to substrate movement.

Allnex New Zealand Ltd state that the Ultratuff 001 FC system is compliant with the Building Act E2 & E3.

This technical data sheet is to be read in conjunction with other relevant technical data sheets. If any doubt or confusion exists please contact Allnex Industries Ltd.



Allnex Construction Products, a Division of Allnex New Zealand Ltd

Auckland - 14 Industry Road Penrose phone: 095836544. Hamilton - 18 Somerset Street Frankton phone: 07-847-8658
 Wellington - 19A Jamaica Drive Grenada North phone: 04-240-0305. Christchurch - 112 Carlyle Street Sydenham phone: 03-366-6802
 Customer Service: 0508-882-288 cs.constructionnz@allnex.com
www.allnexconstruction.com



DISCLAIMER: This information appearing in this Document (**Details**) concerning the product which is the subject of the Document (**Product**) is either based on present technical knowledge and tests done by allnex or tests done by, and data supplied from third parties including you, the customer. Since the actual use by you and by others of the Product is beyond the control of allnex, no warranty or representation, express or implied is made by allnex regarding the suitability for such use, nor does allnex accept any liability arising out of the use by you of other products or materials, whether third party or not, that may be referred to in this Document. allnex recommends that you carry out your own tests as to the suitability of the Product for your purpose, regarding which you accept full responsibility. In addition, if any of the Details appearing in the Document are based upon tests done by, and/or data supplied by any third party, allnex provides no warranties or representations in connection with those Details and you, the customer waives any right you may have against allnex in connection with the accuracy, completeness or otherwise of the Details. The information in this Document is not to be construed as absolutely complete or accurate since additional information may be necessary or desirable when particular or exceptional conditions or circumstances exist or because of applicable laws or government regulations affecting use of the Product. allnex does not provide any warranty or representation to you that the Product does not infringe the intellectual property rights of any third party. All orders accepted shall be subject to the standard conditions of sale of allnex which are on the back of our invoice. In accepting the Product you, the customer acknowledge and agree: **a.)** The Product is or may be of a hazardous nature and that you, the customer, are responsible for the disposal of the container housing the Product in accordance with the requirements and regulations of the relevant supervising government. **b.)** The Product has a limited shelf life and must be stored strictly in accordance with the guidelines and specifications related to it. **c.)** Where the Details relate to Product tested by allnex, those Details are indicative only, regarding which there may be batch to batch variation. **d.)** allnex gives no warranty or representation as to the applicability for the particular use by you, the customer, of the Product and you the customer shall be responsible for ensuring that the Product is fit for your intended use. **e.)** allnex's liability for breach of any term, condition, guarantee or warranty (express or implied and concerning the information in this Document or the Product more generally) including any liability for direct or indirect consequential loss (including indirect loss of profits), is limited to the maximum extent permitted by law and, at allnex's election, to either replacing or repairing the goods or paying the cost of replacing or repairing the goods, or in the case of services, supplying the services again.