

Technical Data Sheet

SWELLSEAL MASTIC WA



DESCRIPTION

Caulk-applied, one-component, hydro-swelling mastic for sealing smooth and rough construction joints and pipe penetrations in wet or underwater applications

Product Description

Swellseal® Mastic WA is a one-component, grey, polyurethane-based, elastic, hydro-swelling mastic, supplied in cartridges and aluminium sausages, for the sealing of expansion joints and around pipe penetrations.

Swellseal Mastic WA cures and swells in the presence of moisture. Curing time is dependent on temperature and humidity conditions, i.e. curing time will reduce if RH and Celsius degrees are higher. Swellseal Mastic WA will become firm in 24-36 hours. Performance is not affected by the curing time.

Product Advantages

- Due to its special formulation, Swellseal® Mastic WA can be applied onto wet surfaces or in underwater applications.
- Suitable for fresh or salt water applications.
- Solvent free.
- Swellseal Mastic WA adheres to concrete, PVC, HDPE, steel, fibre glass, etc.
- The excellent filling and adhesion properties of the product provide a first line filling of cracks and voids, even on lightly humid, smooth or rough surfaces.
- In contact with water Swellseal Mastic WA will expand to about 200% of its original volume.
- Flexible system, which adapts to the irregular surface of the substrate.
- Easy application with a standard caulking gun.
- Durable: will exceed the construction's life.
- Good chemical resistance(*).
- Resistant against petroleum products, mineral and vegetable oils and greases.

(*)For chemical resistance please contact your local Allnex representative.

Application

Swellseal Mastic WA is preferably applied onto a dust-free concrete surface. The surface can be rough or smooth, moist or dry.

When applying Swellseal Mastic WA in underwater or very wet applications, be certain to cast the concrete within 6 hours to prevent premature swelling.

1. Application Method

For 310cc Cartridges

- Break the moisture-proofing aluminium foil on the top of the cartridge and remove the seamer from the bottom. Screw on the nozzle and cut diagonally at the appropriate position. Place the cartridge into caulking gun.

For 600cc Sausages

- Put the sausage in the empty tube of the caulking gun and cut 1cm off the top of the sausage. Close the tube and install the nozzle. Cut the nozzles diagonally at the appropriate position.
- Swellseal Mastic WA is applied in an uninterrupted band (minimum 10mm wide and high), placed with a caulking gun in the middle of the joint or prefab element (minimum concrete cover is 7cm).

In case of fresh concrete, Swellseal Mastic WA should be covered by at least 7cm of concrete on both sides, in order to avoid cracks from the expansion pressure of swelling Swellseal Mastic WA

Field of Application

- Sealing of joints of in-situ cast concrete in wet and underwater applications.
- Sealing joints between precast segments in wet or underwater applications (e.g. manholes, box culverts, cable ducts and pipes).
- Sealing of the locks between sheet piles.

Appearance

Pasty during application and rubbery after curing. Colour: grey.

Technical Data / Properties

Property	Value	Norm
Solids	100%	Test DNC
Uncured		
Viscosity	Gel / Paste	Test DNC
Density (at 20°C)	Approx. 1.45kg / dm ³	DIN 53504
Slump in Vertical Application	< 5mm	Boeing test
Hand Dry (at 20°C and 60% rel. humidity)	10h	Test DNC
Flash Point	> 130°C	Pensky-Martens method
Cured (7 days at 25°C, 10mm thick)		
Swelling Capacity in Contact with Water	Swells to approx. 200% of its original dry volume	Test DNC

Consumption

Nozzle Diameter	Length (Cartridge)	Length (Sausage)
3mm	20 - 25m	40 - 50m
6mm	8 - 10m	16 - 20m
8mm	4 - 5m	8 - 10m
10mm	Approx. 3m	Approx. 6m

Storage

Minimum 12 months in a dry place at temperatures between 5°C and 30°C.

See shelf life information on the packaging.

Accessories

To be ordered separately

- Skeleton caulking gun for cartridges 310mL.
- Caulking gun for sausages 600mL closed tube.
- Nozzle for caulking gun 600mm closed tube.

Health & Safety

For full information consult the relevant Material Safety Data Sheet

Packaging

310ml Cartridges	600ml Sausages
12 per cardboard box	12 per cardboard box
1 pallet = 75 cardboard boxes	1 pallet = 40 cardboard boxes
Weight per cartridge	Weight per sausage
• 0.55kg gross	• 0.99kg gross
• 0.50kg net	• 0.90kg net

Date: July 2018

Replaces: August 2017



Allnex Construction Products, a Division of Allnex New Zealand Ltd

Auckland - 14 Industry Road Penrose phone: 095836544. Hamilton - 18 Somerset Street Frankton phone: 07-847-8658
Wellington - 19A Jamaica Drive Grenada North phone: 04-240-0305. Christchurch - 112 Carlyle Street Sydenham phone: 03-366-6802
Customer Service: 0508-882-288 cs.constructionnz@allnex.com
www.allnexconstruction.com

DISCLAIMER: This information appearing in this Document (**Details**) concerning the product which is the subject of the Document (**Product**) is either based on present technical knowledge and tests done by allnex or tests done by, and data supplied from third parties including you, the customer. Since the actual use by you and by others of the Product is beyond the control of allnex, no warranty or representation, express or implied is made by allnex regarding the suitability for such use, nor does allnex accept any liability arising out of the use by you of other products or materials, whether third party or not, that may be referred to in this Document. allnex recommends that you carry out your own tests as to the suitability of the Product for your purpose, regarding which you accept full responsibility. In addition, if any of the Details appearing in the Document are based upon tests done by, and/or data supplied by any third party, allnex provides no warranties or representations in connection with those Details and you, the customer waives any right you may have against allnex in connection with the accuracy, completeness or otherwise of the Details. The information in this Document is not to be construed as absolutely complete or accurate since additional information may be necessary or desirable when particular or exceptional conditions or circumstances exist or because of applicable laws or government regulations affecting use of the Product. allnex does not provide any warranty or representation to you that the Product does not infringe the intellectual property rights of any third party. All orders accepted shall be subject to the standard conditions of sale of allnex which are on the back of our invoice. In accepting the Product you, the customer acknowledge and agree: a.) The Product is or may be of a hazardous nature and that you, the customer, are responsible for the disposal of the container housing the Product in accordance with the requirements and regulations of the relevant supervising government. b.) The Product has a limited shelf life and must be stored strictly in accordance with the guidelines and specifications related to it. c.) Where the Details relate to Product tested by allnex, those Details are indicative only, regarding which there may be batch to batch variation. d.) allnex gives no warranty or representation as to the applicability for the particular use by you, the customer, of the Product and you the customer shall be responsible for ensuring that the Product is fit for your intended use. e.) allnex's liability for breach of any term, condition, guarantee or warranty (express or implied and concerning the information in this Document or the Product more generally) including any liability for direct or indirect consequential loss (including indirect loss of profits), is limited to the maximum extent permitted by law and, at allnex's election, to either replacing or repairing the goods or paying the cost of replacing or repairing the goods, or in the case of services, supplying the services again.